

## Asphalt Penetration Grade 60/70

No.	Specification		Method	Min	Max	
1	Specific Gravity at 60/60°C		ASTM D-70	1	-	
2	Ductility at 25°C	cm	ASTM D-113	100	-	
3	Flash Point C.O.C		°C	ASTM D-92	200	-
4	Loss on Heating at 5 Hours / 163°C	% wt	ASTM D-6	-	0.4	
5	Penetration at 25°C	0.1 mm	ASTM D-5	60	70	
6	Penetration after Loss on Heating		%	ASTM D-5	75	-
7	Solubility in CCL		% wt	ASTM D-2042	99	-
8	Softening Point Ring and Ball		°C	ASTM D-36	48	58